

BLS | BLANCO LINER SAICA

White Top Testliner C

CEPI code: 72

Characteristics:

- Available exclusively in 22,5 and 24,6 lb/msf.
- Sized paper.
- Suitable for food contact*.

Applications:

- Optimal printing quality.
- Sustainable packaging.
- Light industry.
- Food and beverage.

* For contact conditions and/or special instructions, see our Declaration of Conformity.



100% recycled
and recyclable
papers



BLS | BLANCO LINER SAICA

White Top Testliner C



* For contact conditions and/or special instructions, see our Declaration of Conformity.

target characteristics

TEST	STANDARD	UNIT	BLANCO LINER SAICA	
Nominal basis weight	ISO 536	lb/msf	22,5	24,6
Nominal moisture index	On-line	%	8	8
SCT, CD	ISO 9895	lbf/in	8	9,1
Bursting strength	EN ISO 2758	psi	24	26
COBB-60	EN ISO 535	g/m ²	35	35
Brightness	ISO 2470-1	%	68	68
b*	ISO 5631-2		-3	-3
Roughness (Bendtsen)	ISO 8791-2	ml/min	400	400

guaranteed characteristics

TEST	STANDARD	UNIT	BLANCO LINER SAICA	
Nominal basis weight	ISO 536	lb/msf	22,5	24,6
Mean basis weight			nominal ± 3%	
Nominal moisture index	On-line	%	8	8
Mean moisture index			nominal -1+0,5	
SCT, CD	ISO 9895	lbf/in	6,9	7,4
Bursting strength	EN ISO 2758	psi	21	23
COBB-60	EN ISO 535	g/m ²	50	50
Brightness min-max	ISO 2470-1	%	65-71	
Plybond minimum	TAPPI T 833	ft lbf/in ²	85,7	85,7
Production centre			SP	SP

The index guaranteed values refer to the nominal basis weight.



Access the complete and always updated file.

Valid from May 2025.