

DS | DUOSAICA

Testliner 2 / fluting

CEPI code: 52

Characteristics:

- The lightest and most resistant double use paper on the market.
- Sized paper from 20,5 lb/msf.
- Perfect to reduce the number of cardboard compositions and types of paper in stock.
- Wide range of grammages from 15,4 to 57,3 lb/msf.
- Suitable for food contact*.
- Excellent machinability.

Applications:

- Test liner 2 for outer and inner layers.
- Can be used as fluting.
- Sustainable packaging.
- E-commerce.
- Food and beverage.
- Diverse industrial applications.
- Frozen goods.

* For contact conditions and/or special instructions, see our Declaration of Conformity.



100% recycled
and recyclable
papers

DS | DUOSAICA

Testliner 2 / fluting



* For contact conditions and/or special instructions, see our Declaration of Conformity.

target characteristics

TEST	STANDARD	UNIT	DUOSAICA														
Nominal basis weight	ISO 536	lb/msf	15,4	16,4	17,4	18,4	19,5	20,5	22,5	24,6	26,6	30,7	32,8	41	47,1	57,4	
Nominal moisture index	On-line	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	
CMT 30/50, MD ¹	EN ISO 7263	lbf	20,2	23,4	28,8	32,4	34,2	36	39,6	43,2	46,8	54	57,6	-	-	-	
SCT, CD	ISO 9895	lbf/in	6,9	8	8,6	9,1	9,7	10,3	11,4	12,6	13,7	16	17,1	21	24,6	29,7	
Bursting strength	EN ISO 2758	psi	24	26	27	29	30	32	35	42	45	52	56	70	80	97	
COBB-60	EN ISO 535	g/m ²	-	-	-	-	-	35	35	35	35	35	35	35	35	35	

guaranteed characteristics

TEST	STANDARD	UNIT	DUOSAICA														
Nominal basis weight	ISO 536	lb/msf	15,4	16,4	17,4	18,4	19,5	20,5	22,5	24,6	26,6	30,7	32,8	41	47,1	57,4	
Mean basis weight			← nominal ± 2% →					← nominal ± 3% →					→				
Nominal moisture index	On-line	%	8	8	8	8	8	8	8	8	8	8	8	8	8	8	
Mean moisture index			nominal -1+0,5														
CMT 30/50, MD ¹	EN ISO 7263	lbf	16,9	21,6	25	28,3	29,9	31,5	34,6	37,8	40,9	47,2	50,4	-	-	-	
SCT, CD	ISO 9895	lbf/in	6,3	6,9	8	8	9	9,1	10,3	11,4	12	14,3	14,9	18,9	21,7	26,3	
Bursting strength	EN ISO 2758	psi	22	23	25	26	28	29	32	35	38	44	46	58	67	81	
COBB-60	EN ISO 535	g/m ²	-	-	-	-	-	50	50	50	50	50	50	50	50	50	
Production centre			SP FR UK	SP UK	SP FR UK	SP FR	SP	SP FR PL	SP FR PL	SP FR PL	SP FR PL	SP FR PL	SP FR	FR	FR	FR	

The index guaranteed values refer to the nominal basis weight.

¹ CMT 30/50, MD is not a valid test for weights equal to or greater than 32,8 lb/msf.



Access the complete and always updated file.

Valid from May 2025.