

# ICL | Infinite<sup>∞</sup>lithos

## White Top Testliner Coated

CEPI code: 79

### Characteristics:

- Available in different grammages.
- Internal sizing.
- Suitable for food contact\*.
- High degree of whiteness and smoothness.

### Applications:

- Offset printing sheets and litho-laminating.
- High print quality.
- Alternative to GD2.
- Cleaning and Hygiene industry.
- Food and beverage.
- Diverse industrial applications.
- Trays.

\* For contact conditions and/or special instructions, see our Declaration of Conformity.



100% recycled  
and recyclable  
papers

# ICL | Infinite lithos

## White Top Testliner Coated



\* For contact conditions and/or special instructions, see our Declaration of Conformity.

### target characteristics

TEST	STANDARD	UNIT	INFINITE LITHOS			
Nominal basis weight	ISO 536	lb/msf	32,8	36,9	39,9	43
Nominal moisture index	On-line	%	6	6	6	6
SCT, CD	ISO 9895	lbf/in	17,4	19	20,6	21,7
Bursting strength	EN ISO 2758	psi	51	57	62	67
COBB-60	EN ISO 535	g/m <sup>2</sup>	35	35	35	35
COBB-60 reverse	EN ISO 535	g/m <sup>2</sup>	35	35	35	35
COBB-1800	EN ISO 535	g/m <sup>2</sup>	130	130	130	130
Brightness	ISO 2470-1	%	83	83	83	83
Roughness (Parker)	ISO 8791-4	µm	1,9	2,1	2,1	2,3
Plybond	TAPPI T 833	ft lbf/in <sup>2</sup>	166,5	157	152,3	-

### guaranteed characteristics

TEST	STANDARD	UNIT	INFINITE LITHOS			
Nominal basis weight	ISO 536	lb/msf	32,8	36,9	39,9	43
Mean basis weight						
Nominal moisture index	On-line	%	6	6	6	6
Mean moisture index						
SCT, CD	ISO 9895	lbf/in	15,5	17,5	18,9	19,4
Bursting strength	EN ISO 2758	psi	44	50	54	58
COBB-60	EN ISO 535	g/m <sup>2</sup>	50	50	50	50
COBB-60 reverse	EN ISO 535	g/m <sup>2</sup>	50	50	50	50
COBB-1800	EN ISO 535	g/m <sup>2</sup>	150	150	150	150
Brightness min-max	ISO 2470-1	%	80-86	80-86	80-86	80-86
Roughness (Parker)	ISO 8791-4	µm	2,5	2,7	2,7	3
Plybond minimum	TAPPI T 833	ft lbf/in <sup>2</sup>	119,0	95,2	86	-
Production centre			SP	SP	SP	SP

The index guaranteed values refer to the nominal basis weight.



Access the complete and always updated file.

Valid from May 2025.