

# IN | Infinite innova

## White Top Testliner Light Coated

CEPI code: 78

### Characteristics:

- Available in different grammages from 20,5 lb/msf.
- Spotless whiteness.
- Suitable for food contact\*.
- Allows reducing and grouping absorbent and coated papers into one single paper.

### Applications:

- Suitable for a wide range of flexo and digital printers.
- High printing quality.
- Export fruit and vegetable market.
- Diverse industrial applications.
- Food and beverage.
- Trays.

\* For contact conditions and/or special instructions, see our Declaration of Conformity.



100% recycled  
and recyclable  
papers

# IN | Infinite innova

## White Top Testliner Light Coated



\* For contact conditions and/or special instructions, see our Declaration of Conformity.

### target characteristics

TEST	STANDARD	UNIT	INFINITE INNOVA			
Nominal basis weight	ISO 536	lb/msf	20,5	23,6	27,7	33,8
Nominal moisture index	On-line	%	7,5	7,5	7,5	7,5
SCT, CD	ISO 9895	lbf/in	10,3	12,6	14,9	17,7
Bursting strength	EN ISO 2758	psi	33	42	49	60
COBB-60	EN ISO 535	g/m <sup>2</sup>	40	40	40	-
COBB-1800	EN ISO 535	g/m <sup>2</sup>	-	-	-	130
Brightness	ISO 2470-1	%	76	76	76	76
Roughness (Bendtsen)	ISO 8791-2	ml/min	290	290	310	310
Plybond	TAPPI T 833	ft lbf/in <sup>2</sup>	190,3	190,3	190,3	157

### guaranteed characteristics

TEST	STANDARD	UNIT	INFINITE INNOVA			
Nominal basis weight	ISO 536	lb/msf	20,5	23,6	27,7	33,8
Mean basis weight						
Nominal moisture index	On-line	%	7,5	7,5	7,5	7,5
Mean moisture index						
SCT, CD	ISO 9895	lbf/in	9,1	11,4	13,1	16
Bursting strength	EN ISO 2758	psi	29	37	43	53
COBB-60	EN ISO 535	g/m <sup>2</sup>	50	50	50	-
COBB-1800	EN ISO 535	g/m <sup>2</sup>	-	-	-	150
Brightness min-max	ISO 2470-1	%	73-79			
Roughness (Bendtsen)	ISO 8791-2	ml/min	400	400	450	450
Plybond minimum	TAPPI T 833	ft lbf/in <sup>2</sup>	166,5	166,5	147,5	123,7
Production centre			SP	SP	SP	SP

The index guaranteed values refer to the nominal basis weight.



Access the complete and always updated file.

Valid from May 2025.