

# SKB | SAIKRAFT BLANCO

## White Top Testliner A

CEPI code: 70

### Characteristics:

- Excellent whiteness and smoothness.
- High degree of sizing.
- Suitable for food contact\*.

### Applications:

- High printing quality.
- Sustainable packaging.
- Export fruit and vegetable market.
- Heavy industry.
- Climatic chambers, frozen goods.
- Food and beverage.
- Trays.

\* For contact conditions and/or special instructions, see our Declaration of Conformity.



100% recycled  
and recyclable  
papers

# SKB | SAIKRAFT BLANCO

## White Top Testliner A



\* For contact conditions and/or special instructions, see our Declaration of Conformity.

### target characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO		
Nominal basis weight	ISO 536	lb/msf	25,6	28,7	34,8
Nominal moisture index	On-line	%	8	8	8
SCT, CD	ISO 9895	lbf/in	13,7	15,4	18,3
Bursting strength	EN ISO 2758	psi	47	53	62
COBB-60	EN ISO 535	g/m <sup>2</sup>	25	25	25
COBB-1800	EN ISO 535	g/m <sup>2</sup>	100	100	100
Brightness	ISO 2470-1	%	76	76	76
b*	ISO 5631-2		-9	-9	-9
Roughness (Bendtsen)	ISO 8791-2	ml/min	300	325	350

### guaranteed characteristics

TEST	STANDARD	UNIT	SAIKRAFT BLANCO		
Nominal basis weight	ISO 536	lb/msf	25,6	28,7	34,8
Mean basis weight					
Nominal moisture index	On-line	%	8	8	8
Mean moisture index					
SCT, CD	ISO 9895	lbf/in	12	13,7	16,6
Bursting strength	EN ISO 2758	psi	42	47	54
COBB-60	EN ISO 535	g/m <sup>2</sup>	50	50	50
COBB-1800	EN ISO 535	g/m <sup>2</sup>	150	150	150
Brightness min-max	ISO 2470-1	%	73-79	73-79	73-79
Plybond minimum	TAPPI T 833	ft lbf/in <sup>2</sup>	166,5	166,5	142,8
Production centre			SP	SP	SP

The index guaranteed values refer to the nominal basis weight.



Access the complete and always updated file.

Valid from May 2025.